



TEST REPORT

NUMBER: TXT381758

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

| | | | <u>PROVIDED REQUIREMENTS MARKED</u> |
|---|--|------------|---|
| 1 | FIBRE IDENTIFICATION (ISO 1833) : | | |
| | <u>(A)</u> | <u>(B)</u> | |
| | NYLON | 100% | 100% NYLON |
| 2 | DIMENSIONAL STABILITY TO WASHING (EN26330 + EN25077, WASCATOR WASHING MACHINE-FRONT-LOADING HORIZONTAL ROTATING DRUM TYPE, TEST PROGRAMME 6A, 40°C WITH 2 KG LOAD, IN 0.08% IEC REFERENCE DETERGENT AND 0.02% SODIUM PERBORATE SOLUTION, FOLLOWED BY TUMBLE DRY) : | | |
| | <u>AFTER ONE WASH</u> | | |
| | WARP(%) | -1.4 | -2.0 |
| | WEFT(%) | -1.4 | -1.4 |
| | | | +/-3% |
| | REMARK : (+) MEANS EXTENSION AND (-) MEANS SHRINKAGE | | |
| 3 | COLOR FASTNESS TO WASHING (EN ISO/105 C06 A2S-1994, SINGLE TEST, 30 MINUTES MECHANICAL WASH AT 40°C IN 0.4% ECE REFERENCE DETERGENT AND 0.1% SODIUM PERBORATE SOLUTION WITH 10 STEEL BALLS): | | |
| | COLOUR CHANGE | 4-5 | 4-5 |
| | COLOUR STAINING | | 4 |
| | | | 3-4 |
| | -ACETATE | 4-5 | 4-5 |
| | -COTTON | 4-5 | 4-5 |
| | -NYLON | 4-5 | 4-5 |
| | -POLYESTER | 4-5 | 4-5 |
| | -ACRYLIC | 4-5 | 4-5 |
| | -WOOL | 4-5 | 4-5 |
| 4 | COLOUR FASTNESS TO RUBBING AS RECEIVED (EN ISO/105 X12-1993) | | |
| | : | | |
| | WET | 4-5 | 4-5 |
| | | | 3 |
| 5 | COLOUR FASTNESS TO WATER (EN ISO 105 E01-1994) : | | |
| | COLOUR CHANGE | 4-5 | 4-5 |
| | COLOUR STAINING | | 4 |
| | | | 3-4 |
| | -ACETATE | 4-5 | 4-5 |
| | -COTTON | 4-5 | 4-5 |
| | -NYLON | 4-5 | 4-5 |
| | -POLYESTER | 4-5 | 4-5 |
| | -ACRYLIC | 4-5 | 4-5 |
| | -WOOL | 4-5 | 4-5 |
