

WENGCORP LTD.

The following sample was submitted and identified by the client as:

SAMPLE DESCRIPTION: ONE SAMPLE OF WOVEN FABRIC 400DX500D/62X38 W/COATING
IN BLACK

SAMPLE RECEIVING DATE: DEC. 21, 2004

TEST STARTING DATE: DEC. 28, 2004

Test Performed: Selected test(s) as requested by applicant.

Test Results:

Water Vapor Transmission (WVT) (ASTM E-96 - 00 Procedure BW Inverted Water Method)


g/m²/24 hrs 5189.3Tested condition: X1.7.4 Gasketed type cup, area: 0.003 m²

Temperature : 23±2°C

Relative Humidity : 50±2%

Note : Back side to water.

*** End of Report ***

Signed for and on behalf of
SGS Taiwan Ltd.

Wu Shu Yi, Jessica

Asst. Supervisor

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification, and Jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此報告是遵照本公司訂定之通用服務條款所製作發放。請注意此條款列印於背面。將本公司之義務、免責、管轄權皆明確規範之。此報告結果除非另有說明僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。

TW 1397503